

Trovidur® PN

Product characteristics

- Uniform physical properties
- High resistance to acids, lyes and salt solutions
- Flame retardant, self-extinguishing after removal of flame

Typical field of application

- Mechanical engineering
- Chemical engineering and tank building
- Electrical and electronic industries

	Test method	Unit	Value
General properties			
Density	DIN EN ISO 1183-1	g/cm ³	1,47
Water absorption	DIN EN ISO 62	%	≤ 3
Flammability (Thickness 3 mm / 6 mm)	UL 94		V0
Mechanical properties			
Elongation at break	DIN EN ISO 527	%	15
Tensile modulus of elasticity	DIN EN ISO 527	MPa	3000
Notched impact strength (charpy)	DIN EN ISO 179	kJ/m ²	4
Shore hardness	DIN EN ISO 868	scale D	82
Thermal properties			
Thermal conductivity	DIN 52612-1	W / (m * K)	0,16
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ K ⁻¹	60-80
Heat deflection temperature	DIN EN ISO 306, Vicat B	°C	73
Electrical properties			
Dielectric constant	IEC 60250		3,20
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,020
Volume resistivity	IEC 60093	Ω *cm	>10 ¹⁵
Surface resistivity	IEC 60093	Ω	>10 ¹³

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.